



Material & Engineering Laboratory-Kaohsiung

Test Report

REPORT NO : KV-2004-7-0023XA

PAGE NO : 1 OF 1

DATE : JUL. 01, 2004

CLIENT

NEW PRISMATIC ENTERPRISE CO., LTD.

CARGO

Glow In the Dark Material YA-2

SAMPLED BY

Marc Yu

SAMPLE RECEIVED DATE

JUL. 01, 2004

SAMPLE TESTED DATE

JUL. 01, 2004

REMARK

The information mentioned in the above section is provided by testing applicant(Exclude tested date)


TEST RESULTS :

Test Item	Test Method	Test Result
Brightness (mcd/m ²)	Refer to JIS 9107	At 0 min. : 1773.1 After 10 min. : 401 After 30 min. : 140.5 After 60 min. : 65.5 After 120 min. : 27.9 Based on the curve trend, after 4108 min., the brightness was approach to 0.32mcd/m ²

Remark : Sample Size : 20g
 Appearance Color : Yellow and Green
 Radioactive Color : Yellow and Green
 Excitation Time : 20min.
 Light Type : D65
 The Measurement Instrument of Brightness : Colorimeter k-10
 The Measurement Instrument of Light : Digital Lux/light
 Atmosphere Temperature : 30°C

---- o O o ----

The value of required specifications are for reference only.
Conformity judgement is the Applicant's final verdict.



Signed for and on behalf of
SGS Taiwan Ltd.

TW 0067131

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf. Attention is drawn to the limitations of liability, indemnification, and Jurisdictional issues defined therein. The results shown in this test report refer only to the sample(s) tested unless otherwise stated. This Test Report cannot be reproduced, except in full, without prior written permission of the Company. 此報告是遵循本公司訂定之通用服務條款所製作發放。請注意此條款列印於背面，將本公司之義務，免責，管轄權皆明確規範之。此報告結果除非另有說明僅對檢驗之樣品負責。本報告未經本公司書面許可，不可部份複製。